

DESCRIPTION

Alkathene LDD203 is a low density polyethylene designed for a variety of medium to heavy gauge (50-150µm) general purpose film applications. Alkathene LDD203 is formulated with a process stabilisation and antiblock additive package but contains no slip additives.

APPLICATION

Film Extrusion: Alkathene LDD203 is intended for heavy duty bags, shrink film and other medium to heavy gauge films that require antiblock.

FOOD CONTACT / PRODUCT SAFETY

For food contact information please refer to the Regulatory Data Sheet at genos.com. For product safety information please refer to the Safety Data Sheet at genos.com.

Polymer Properties	Value ¹	Units	Test Method
Melt Index @ 190°C, 2.16 kg	0.45	g/10 min	ASTM D1238
Density ²	0.922	g/cm ³	ASTM D1505

Film Properties ³	Value ¹	Units	Test Method	
Haze	10	%	ASTM D1003	
Gloss, 45°	62	GU	ASTM D2457	
Dart Drop Impact (F ₅₀)	140	g	ASTM D1709	
Tear Strength	MD TD	3.7 2.5	N N	ASTM D1922
Tensile Strength at Yield ⁴	MD TD	12 11	MPa MPa	ASTM D882
Tensile Strength at Break ⁴	MD TD	26 20	MPa MPa	ASTM D882
Elongation at Break ⁴	MD TD	330 730	% %	ASTM D882
2% Secant Modulus ⁵	MD TD	160 190	MPa MPa	ASTM D882

1. Typical values - not to be construed as specifications.
2. Base resin density; antiblock additive adds 0.001 – 0.002 g/cm³.
3. Film Properties have been measured on 50µm gauge film extruded at Qenos (2.0 to 1 blow-up ratio).
4. At 500 mm/min cross head speed.
5. At 20 mm/min cross head speed.

For up to date information, refer to genos.com

This information is offered solely for your consideration, investigation, verification and shall not be construed as a warranty or representation for which Qenos Pty Ltd assumes legal liability, except to the extent that such liability is imposed by legislation and cannot be excluded. Values quoted are the result of tests on representative samples, and the product supplied may not conform in all respects. Qenos Pty Ltd reserves the right to make any improvements or amendments to the composition of any grade or product without alteration to the code number. In using Qenos Pty Ltd's products, you must establish for yourself the most suitable formulation, production method and control tests, to ensure the uniformity and quality of your product in compliance with all laws. Qenos Pty Ltd ACN 054 196 771 is the registered user of the Qenos Logo which is registered trademark of Qenos Pty Ltd. "Alkathene" is a trademark of Qenos Pty Ltd.