

Technical Data Sheet Linear Low Density Polyethylene

## **DESCRIPTION**

LL525 is a hexene copolymer linear low density polyethylene, designed for high quality cast film applications. LL525 is formulated with stabilisation additives, but contains no other additives.

## **APPLICATION**

<u>Film Extrusion</u>: LL525 is intended for cast film applications such as nappy film and bubble wrap. Addition of a UV stabiliser should be considered where the intended application involves intermittent to extended exposure to sunlight.

## FOOD CONTACT / PRODUCT SAFETY

For food contact information please refer to the Regulatory Data Sheet at <u>genos.com</u>. For product safety information please refer to the Safety Data Sheet at <u>genos.com</u>.

Polymer Properties	Value <sup>1</sup>	Units	Test Method
Melt Index @ 190°C, 2.16 kg	2.5	g/10 min	ASTM D1238
Density	0.935	g/cm <sup>3</sup>	ASTM D1505

Film Properties <sup>2</sup>		Value <sup>1</sup>	Units	Test Method
Haze		4	%	ASTM D1003
Gloss, 45°		79	GU	ASTM D2457
Dart Drop Impact (F <sub>50</sub> )		60	g	ASTM D1709
Tensile Strength at Yield <sup>3</sup>	MD TD	15 15	MPa MPa	ASTM D882
Tensile Strength at Break <sup>3</sup>	MD TD	31 28	MPa MPa	ASTM D882
Elongation at Break <sup>3</sup>	MD TD	750 840	% %	ASTM D882

1. Typical values - not to be construed as specifications.

2. At 500 mm/min cross head speed.

3. Film properties measured on 25µm gauge film extruded on commercial cast line (230°C melt temperature)

For up to date information, refer to genos.com

This information is offered solely for your consideration, investigation, verification and shall not be construed as a warranty or representation for which Qenos Pty Ltd assumes legal liability, except to the extent that such liability is imposed by legislation and cannot be excluded. Values quoted are the result of tests on representative samples, and the product supplied may not conform in all respects. Qenos Pty Ltd reserves the right to make any improvements or amendments to the composition of any grade or product without alteration to the code number. In using Qenos Pty Ltd's products, you must establish for yourself the most suitable formulation, production method and control tests, to ensure the uniformity and quality of your product in compliance with all laws. Qenos Pty Ltd ACN 054 196 771 is the registered user of the Qenos Logo which is registered trademark of Qenos Pty Ltd. "Alkatuff" is a trademark of Qenos Pty Ltd.



