

DESCRIPTION

Alkatuff LL755 is a hexene LLDPE material specifically designed for rotational moulding applications that require excellent ESCR, chemical resistance*, stiffness and toughness. Alkatuff LL755 does not contain UV stabiliser.

APPLICATION

Alkatuff LL755 is a general purpose rotational moulding grade, uses of which include water and agricultural tanks, leisure craft and playground equipment. For outdoor applications, an appropriate UV stabilisation package should be added. Alkatuff LL755 complies with the non UV base resin requirements of AS/NZS 4766 Rotationally moulded buried, partially buried and non-buried storage tanks for water and chemicals.

FOOD CONTACT / PRODUCT SAFETY

For food contact information please refer to the Regulatory Data Sheet at qenos.com. For product safety information please refer to the Safety Data Sheet at qenos.com.

Polymer Properties	Value ¹	Units	Test Method
Melt Index @ 190°C, 2.16 kg	5.0	g/10 min	ASTM D1238
Density	0.935	g/cm ³	ASTM D1505

Moulding Properties	Value ¹	Units	Test Method
Melting Point	127	°C	ASTM D3418
Thermal Stability	Pass	-	AS/NZS 4766
Tensile Strength at Yield ²	17.5	MPa	ASTM D638
Flexural Modulus (1% Secant) ³	700	MPa	ASTM D790B
ESCR F ₅₀ (Condition A, 100% Igepal)	>1000	hrs	ASTM D1693
Contact with Drinking Water	Pass	-	AS/NZS 4020
Hydrostatic Design Basis	6.89 ⁴	MPa	ASTM D2837

1. Typical values - not to be construed as specifications.
2. At 50 mm/min crosshead speed.
3. At 12.7 mm/min crosshead speed.
4. A service factor must be applied in accordance with AS/NZS 4766.

For up to date information, refer to qenos.com

* The level of chemical resistance is a function of product design and environmental conditions. Contact Qenos for further information



This information is offered solely for your consideration, investigation, verification and shall not be construed as a warranty or representation for which Qenos Pty Ltd assumes legal liability, except to the extent that such liability is imposed by legislation and cannot be excluded. Values quoted are the result of tests on representative samples, and the product supplied may not conform in all respects. Qenos Pty Ltd reserves the right to make any improvements or amendments to the composition of any grade or product without alteration to the code number. In using Qenos Pty Ltd's products, you must establish for yourself the most suitable formulation, production method and control tests, to ensure the uniformity and quality of your product in compliance with all laws. Qenos Pty Ltd ACN 054 196 771 is the registered user of the Qenos Logo which is registered trademark of Qenos Pty Ltd. "Alkatuff" is a trademark of Qenos Pty Ltd.

